

LUKOIL THERMOFLEX EP 2-180

Multipurpose High-Temperature Complex Lithium Grease

DESCRIPTION

LUKOIL® THERMOFLEX EP 2-180 is a multipurpose high-temperature grease based on complex lithium soap, highly refined mineral oil blend with low evaporation, good stability to oxidation. The grease contains high-performance additive package.

LUKOIL® THERMOFLEX EP 2-180 grease has excellent tribological features and can operate under heavy mechanical loads and in frequent contact with water. Service temperature range is from - 30 up to +160°C.

LUKOIL® THERMOFLEX EP 2-180 grease is blue in color and has moderate soft consistency and homogeneous structure.



ADVANTAGES:

- Excellent high-temperature properties
- Excellent load carrying capacity at low temperatures
- High water resistance
- Excellent adhesion
- Long-term service life
- Very good anti-corrosion properties
- Resistance to shock and vibrational loads

COMPOSITION:

- Highly refined mineral oil
- Complex lithium soap
- Anti-wear (AW) / extreme pressure (EP), anti-corrosion, anti-oxidation additives

APPLICATION IN UNITS:

- Rolling bearings operating for a long time while on high speeds and under heavy loads, exposed to intensive vibrations and at high temperatures
- Sliding bearings, guideways
- Bushings, swivels, units where sealing effect of the lubricant is required to prevent dirt, dust and water from getting inside

APPLICATION EXAMPLES:

- Wheel bearings of the passenger and commercial vehicles
- Widely used in bearings of industrial fans, electric motors, couplings, clutches, shafts, compressors, pumps and other industrial equipment
- Centralized lubrication systems in construction, mining, lumbering, and agricultural machinery where use of NLGI 2 class lubricants is recommended

LUKOIL THERMOFLEX EP 2-180. Edition 04/18 replaces edition 10/16

This product is manufactured according to **STO 65561488-013-2014**

LUKOIL® THERMOFLEX EP 2-180

TYPICAL PROPERTIES

Standard*	Property	Unit	Value
DIN 51502	Marking according to DIN 51502		KP2P-30
ISO 6743-9	Marking according to ISO 6743-9		L-XCEHB 2
	Color	Blue to navy-blue	
	Service temperature range	°C	-30 to +160
DIN 51818	NLGI consistency class		2
ISO 2137	Worked penetration (mixed, 60 double strokes)	mm/10	265-295
ISO 2137	Penetration change at 25 °C after 10000 cycles	mm/10	±10
DIN 51562	Base oil viscosity at 40°C	mm ² /s	180
DIN 51562	Base oil viscosity at 100°C	mm ² /s	16
ISO 2176	Drop point	°C	>260
ASTM D2596	Weld load (4-ball machine test) at 25°C	N	3479
ASTM D2266	Wear scar (4-ball machine test)	mm	0,4
DIN 51802	Corrosion degree (rolling bearings, distilled water)		0-0
ASTM D4048	Corrosion degree (copper strip)		1a

*DIN: Deutsche Industrie Norm

ISO: International Standardization Organization

ASTM: American Society for Testing and Materials.

HOW TO USE

This grease can be applied manually with brush or spatula, as well as through individual lubrication systems.

USABLE LIFE AND STORAGE

When stored in the original unopened containers in a dry place, this product has a shelf life of at least 36 months from the date of production.

HANDLING PRECAUTIONS

This product doesn't contain any toxic ingredients. During storage, transportation, and application of this product, the safety rules for handling mineral lubricating materials and the environment protection regulations must be observed.

For further information on how to use LUKOIL® products, please refer to the product MSDS.

TECHNICAL SUPPORT

For correct selection of lubricating materials to meet your needs, and to get more detailed information on the products, as well as if you have any other questions, we recommend you to contact our technical support service specialists by e-mail: grease.support@lukoil.com

LUKOIL THERMOFLEX EP 2-180. Edition 04/18 replaces edition 10/16

Product technical properties are typical and can vary in strong limits.

Due to research and development of science and technology technical properties of product indicated in this Technical Data Sheet can be changed without notification.